

Local Quantum Criticality of an Iron-Pnictide Tetrahedron

T. Tzen Ong¹ and Piers Coleman^{1,2}

¹Center for Materials Theory, Department of Physics & Astronomy, Rutgers University, Piscataway NJ 08854, USA

²Department of Physics, Royal Holloway, University of London, Egham, Surrey TW20 0EX, UK

(Dated: November 18, 2011)

Motivated by the close correlation between transition temperature (T_c) and the tetrahedral bond angle of the As-Fe-As layer observed in the iron-based superconductors, we study the interplay between spin and orbital physics of an isolated iron-arsenide tetrahedron embedded in a metallic environment. Whereas the spin Kondo effect is suppressed to low temperatures by Hund's coupling, the orbital degrees of freedom are expected to quantum mechanically quench at high temperatures, giving rise to an overscreened, non-Fermi liquid ground-state. Translated into a dense environment, this critical state may play an important role in the superconductivity of these materials.

The discovery of superconductivity with $T_c = 26\text{K}$ in LaFeAsO by Hosono *et. al.* [1] has opened up a new field of iron-based high temperature superconductors (SCs). Experimental studies suggest a range of electron correlation effects. For example, in the undoped parent antiferromagnets, neutron scattering studies show a small ordered moment in the pnictides, but a significantly larger moment in the chalcogenides[2]. Similarly, optical studies in BaFe_2As_2 and SrFe_2As_2 indicate a spin-density wave (SDW) gap [3] normally associated with itinerant electrons while optical studies in LaFePO [4] and ARPES results in $\text{FeSe}_{0.42}\text{Te}_{0.58}$ [5, 6] suggest significant correlation effects. This diversity of behavior has prompted an active debate on the role of electron correlation effects. While some groups favor a more localized theoretical description[7, 8], many theoretical treatments[9] have favored an itinerant, multi-band description.

One aspect of these systems that is poorly understood, concerns the strong connection between the many body physics and solid-state chemistry[10]. In these superconductors the iron atom sits inside a tetrahedral cage of pnictide (As,P) or chalcogenide (Te,Se) atoms. Experiments show that the transition temperature is maximal when the bond-angles most closely approximate that perfect tetrahedron ($\theta(\text{As-Fe-As}) = 109.5^\circ$)[11, 12]. More recent studies show [13] that when the tetrahedra are compressed along the c-axis, the superconducting gap becomes anisotropic, and measurements also show the presence of line nodes [14].

Motivated by these issues, here we develop a theory for an isolated iron-tetrahedron embedded within a conduction sea. One of our key observations, is that in addition to their spin physics, the iron-based tetrahedra develop an orbital degree of freedom associated with the degenerate e_g orbitals. For conventional transition metal ions, the Hund's coupling J_H locks the unpaired electrons together into a high spin configuration, exponentially suppressing the spin-Kondo temperature to low temperatures according to an effect discovered by Schrieffer [15]. Here we show that unlike their spin counterparts, orbital fluctuations are not subject to the ‘‘Schrieffer effect’’, giving rise to a unique situation in which the orbital degrees

of freedom behave as fluctuating quantum mechanical variables that result in an incoherent ‘‘non-Fermi liquid’’ ground-state. While departures from perfect tetragonal-ity will re-establish the Fermi liquid, a large temperature range of incoherent metal behavior is expected to remain. We assume that the FeAs tetrahedron contains an Fe^{2+}




FIG. 1. Phase diagram of single Fe in an As tetrahedron. At $T \sim J_H$, the Hund's coupling locks the spins of the Fe atom into an $S = 2$ state, and the orbital Kondo effect flows to strong coupling, giving rise to a Marginal Fermi Liquid over-screened state at $T \sim T_K^{\text{orbital}}$. The dangerously irrelevant spin Kondo interaction finally drives the system to an over-screened spin Kondo ground state at T_K^{spin} . θ is the deviation away from perfect tetrahedral symmetry, where $\theta_c = 109.5^\circ$, and will break the $SU(2)^{\text{orb}}$ symmetry and restore Fermi liquid behaviour.

ion in an $3d^6$ configuration. In a tetrahedral environment, the five d -electron orbitals are split by the crystal field Δ_{CF} into three degenerate upper t_{2g} orbitals and the two degenerate lower e_g orbitals, as shown in Fig. 2. When the tetrahedron is perfect, the unpaired electron in the lower e_g orbitals can sit in the $d_{3z^2-r^2}$ or the $d_{x^2-y^2}$ orbital, giving rise to an unquenched orbital degree of freedom. Using a perturbative renormalization group treatment, we show that at high energies, orbital

Kondo fluctuations dominate and the system flows to an over-screened orbital Kondo fixed point. The residual low energy orbital degrees of freedom condense into a single Majorana fermion that scatters electrons to produce a Marginal Fermi liquid (MFL). By analyzing the physics of this state using a strong coupling expansion, we show that the subsequent low temperature spin Kondo effect is also overscreened, so that the the FeAs tetrahedron is a critical system down to the lowest temperatures. The lo-




FIG. 2. Crystal field splitting of the d -electron orbitals in a tetrahedron into the upper t_{2g} and lower e_g orbitals. The lower diagram shows effect of compression along the c -axis, which lifts the two-fold degeneracy in the e_g orbitals.

cal physics of a single FeAs tetrahedron can be modelled by an Anderson model $H = H_0 + H_A$ that describes the hybridization of Hund's coupled d -electrons in five electron channels $\Gamma \in [t_{2g}, e_g]$, where

$$\begin{aligned}
 H_0 &= \sum_{\vec{k}\sigma\Gamma} \epsilon_{\vec{k}} c_{\vec{k}\Gamma\sigma}^\dagger c_{\vec{k}\Gamma\sigma}, \\
 H_A &= \sum_{\Gamma \in [t_{2g}, e_g]} (V_\Gamma d_{\Gamma\sigma}^\dagger \psi_{\Gamma\sigma} + \text{H.c.}) + \epsilon_\Gamma d_{\Gamma\sigma}^\dagger d_{\Gamma\sigma} \\
 &+ \sum_{\Gamma \in [t_{2g}, e_g]} +U n_{\Gamma\sigma} n_{\Gamma\bar{\sigma}} - J_H |\vec{S}|^2
 \end{aligned} \quad (1)$$

Here, $\vec{S} = 1/2 \sum_\Gamma d_{\Gamma\alpha}^\dagger \vec{\sigma}_{\alpha\beta} d_{\Gamma\beta}$, is the total spin of the d -electrons, ϵ_Γ the energy of the crystal field level Γ , while $\psi_{\Gamma\alpha}^\dagger = \sum_{\vec{k}} c_{\vec{k}\Gamma\alpha}^\dagger$ creates a conduction electron at the origin in channel Γ . We shall assume that the Hubbard interaction, U , is the largest scale in the problem, with a hierarchy of energy scales given by $U > D > J_H > V_\Gamma$, where D is the electron bandwidth.

The effective low energy Hamiltonian can be derived by a Schrieffer-Wolff transformation, and is given by $H =$

$H_0 + H_K$, where

$$\begin{aligned}
 H_K &= \frac{J_2}{4S} \vec{S} \cdot \vec{\sigma}_{t_{2g}}(0) \\
 &+ \frac{J}{2} \left(\frac{1}{2S} \vec{S} \cdot \vec{\sigma}_{e_g}(0) + \frac{1}{2} \mathbb{1} \right) \left(\vec{T} \cdot \vec{\tau}(0) + \frac{1}{2} \mathbb{1} \right)
 \end{aligned} \quad (2)$$

where $\vec{\sigma}_\Gamma(0) = \frac{1}{2} \psi_{\Gamma\alpha}^\dagger \vec{\sigma}_{\alpha\beta} \psi_{\Gamma\beta}$ is the conduction electron spin-density at the origin in channel Γ , while

$$\vec{\tau}(0) = \frac{1}{2} \sum_{\Gamma\Gamma' \in e_g} \psi_{\Gamma\alpha}^\dagger \vec{\tau}_{\Gamma\Gamma'} \psi_{\Gamma'\alpha} \quad (3)$$

describes the orbital moment of the conduction electrons in the e_g channel. The Kondo coupling in each channel is given by $J_\Gamma = 2|V_\Gamma|^2(1/|\epsilon_\Gamma| + 1/(U + \epsilon_\Gamma))$.

The first term in H_K describes the Kondo interaction in the t_{2g} orbitals, while the second term, reminiscent of a local ‘‘Kugel Khomskii’’ interaction[22, 23], describes the mixing of e_g spin and orbital degrees freedom: for $S = 1/2$, this is the well-known $SU(4)$ Kondo interaction, but for large Hund's coupling, the system is locked into a high spin state with $S = 2$. Projected into this subspace, the interaction in the e_g orbitals factorizes into spin and orbital Kondo interactions.

One of the effects of the projection into the high-spin manifold is an S -fold reduction of the spin Kondo coupling, $J_S = J/4S$ but strikingly, the the strength of the orbital Kondo interaction is unaffected. This means that the Hund's interaction will exponentially suppress the spin Kondo effect down to a lower scale $T_K^{spin}/D \sim (T_K^{orb}/D)^{2S}$, as in conventional transition metal ions, while leaving the orbital Kondo effect unaffected. This schism between the orbital and spin Kondo effect drastically affects the physics, as we now confirm from a renormalization analysis.

$$\begin{aligned}
 H_K &= \frac{J}{2} \vec{T} \cdot \vec{\tau} + \frac{J}{4S} \vec{S} \cdot \vec{\sigma}_{e_g} \\
 &+ \frac{J}{2S} (\vec{S} \cdot \vec{\sigma}_{e_g}) (\vec{T} \cdot \vec{\tau}) + \frac{J_2}{4S} \vec{S} \cdot \vec{\sigma}_{t_{2g}}
 \end{aligned} \quad (4)$$

A perturbative RG treatment of Eq. 4 is carried out, with the Feynman diagrams shown in Fig. 3; and the dimensionless coupling constants are defined as $g_S = \frac{J}{4S} \rho(E_F)$, $g_T = \frac{J}{2} \rho(E_F)$ and $g_m = \frac{J}{2S} \rho(E_F)$. Since there are no orbital fluctuations in the t_{2g} orbitals, we just obtain the standard Kondo result for J_2 . In the e_g channels, there are contributions to the renormalization of g_S and g_T from the ‘‘mixed’’ Kondo term, which are proportional to $|\vec{T}|^2 g_m^2$ and $|\vec{S}|^2 g_m^2$ respectively, and the beta-functions are,

$$\begin{aligned}
 \beta_{g_T} &= -2g_T^2 - 2S(S+1)g_m^2 \\
 \beta_{g_S} &= -2g_S^2 - \frac{3}{2}g_m^2 \\
 \beta_{g_m} &= 8g_m^2 - 4g_m g_T - 4g_m g_S
 \end{aligned} \quad (5)$$




FIG. 3. The two one loop diagrams that contribute to the renormalization of g_T , g_S and g_m . Here, the operator O corresponds to the spin, iso-spin or “mixed” Kondo operator, i.e. $\vec{O} \in [\vec{\sigma}, \vec{\tau}, \vec{\sigma}\vec{\tau}]$, and the dashed line corresponds to the local conduction electron propagator $G^{(c)}(\omega)$.

Since both g_S and g_m are of order $O(1/S)$, while g_T is of order $O(1)$, clearly β_{g_T} is of order $O(1)$ and $\beta_{g_m} \sim O(1/S)$ and $\beta_{g_S} \sim O(1/S^2)$. Hence, g_T is the most relevant perturbation, and the system initially flows towards the over-screened orbital fixed point at $T = T_K^{orb}$. The key result is that the quenching of the orbital degrees freedom leaves behind an unscreened $S = 2$ spin moment coupled to five independent screening channels.

While orbital fluctuations are quenched below T_K^{orb} , we might expect that only remaining local degrees of freedom would be the local $S = 2$ spin, Kondo coupled to the five channels. From this point-of-view, the effective Hamiltonian will be an overscreened five-channel $S = 2$ Kondo model consisting of the first two terms in Eq. 6 below.

$$H = H_0 + \sum_{\Gamma} J_{\Gamma} \vec{S} \cdot \psi_{\Gamma\alpha}^{\dagger} \frac{\vec{\sigma}_{\alpha\alpha'}}{2} \psi_{\Gamma\alpha'} + H_{res} \quad (6)$$

However, this reasoning ignores certain subtle low-energy excitations generated by the orbital Kondo effect, that we have anticipated by including a further term H_{res} . In fact, the orbital Kondo effect couples to the spin up and spin down conduction electrons, and is thus overscreened. This gives rise to a well-documented MFL state with a zero-energy excitation described by a single Majorana fermion $\phi(0)$ [17–19]. The interaction with the spin and conduction electrons must be taken into account. This requires decoupling the spin and orbital sectors of the e_g conduction electrons in terms of itinerant Majorana fermions, $(\psi^0, \vec{\psi})$, and $(\chi^0, \vec{\chi})$, which respectively carry the spin and orbital quantum numbers.

In the strong-coupling limit, the Hamiltonian is projected into the degenerate orbital singlets subspace. Clearly, the spin Kondo term depends only on the ψ fermions that carry spin, whereas the mixed Kondo term depends on both ψ and χ fermions as it can mix the

two singlet states. The Majorana fermion at the origin, $\phi(0) = \chi^1(0)\chi^2(0)\chi^3(0)$ is a three-fermion composite, and it couples to the χ fermions at the neighbouring site via the kinetic term; thus the first non-trivial term is 3^{rd} -order, $\tilde{\alpha} = 3t^3/4g_T^2$. The effective strong coupling Hamiltonian, $\tilde{H}$, is therefore,

$$\begin{aligned} \tilde{H} = it \sum_{n=1}^{\infty} \sum_{a=0}^3 [\psi^a(n+1)\psi^a(n) + \chi^a(n+1)\chi^a(n)] \\ + \alpha\phi(0)\chi^1(1)\chi^2(1)\chi^3(1) - i\frac{g_S}{2}\vec{S} \cdot (\vec{\psi}(0) \times \vec{\psi}(0)) \\ + \frac{g_m}{2}\psi^0(0)\vec{S} \cdot \vec{\psi}(0)\phi(0)\chi^0(0) + H_{0,t_{2g}} + H_{K,t_{2g}}(7) \end{aligned}$$

where $H_{0,t_{2g}}$ and $H_{K,t_{2g}}$ are the kinetic energy of the conduction electrons and the Kondo interaction in the t_{2g} channel. Dimensional analysis shows that the canonical dimensions of the Majorana fermions and coupling constants are $[\psi]_L = [\chi]_L = -\frac{1}{2}$, and $[g_S]_L = 0$ and $[g_m]_L = \frac{1}{2}$. Therefore g_m is irrelevant around the strong coupling fixed point.

We then carried out a one loop calculation of the renormalization of g_S . At $T = 0$, the local Majorana fermions propagators $G^{\chi}(\tau) = G^{\psi}(\tau) \sim \frac{1}{\tau}$, and $G^{\phi}(\tau) = \frac{1}{2}sgn(\tau)$, which means that at one loop order, there is a $(g_S/2)^2 \ln\Lambda$ correction to g_S , where Λ is an UV cut-off, whereas g_m does not contribute. This shows that the spin Kondo coupling, g_S , is marginally relevant around the strong coupling fixed point, and will finally drive the system into an over-screened spin and orbital Kondo ground state with a different MFL. Therefore, the system is a quantum-critical incoherent metal down to 0 K.

Fig. 4 shows the renormalization flows for the system. The perfectly-screened Fermi liquid fixed point lies in plane I, defined by $\beta_{g_m} = 0$, along the line $\beta_{g_T} = \alpha(S)g_S$, where $\alpha(S = 2) = 12.2$. For $S = 1/2$, $\alpha(S) = 1$ and we recover the SU(4) Fermi liquid fixed point, which is characterized by perfect screening of the spin and orbital degrees of freedom.

The FeAs tetrahedron initially flows towards the over-screened orbital Kondo fixed point, where orbital fluctuations are quenched at T_K^{orb} . It will then cross-over to an over-screened orbital and spin Kondo fixed point at a lower temperature T_K^{spin} , and two different MFLs arise at T_K^{orb} and T_K^{spin} due to over-screened orbital and spin Kondo physics respectively. The over-screened spin Kondo fixed point with n channels lies at $g^* = \frac{2}{n}(1 - \frac{2}{n}\ln 2)$ [20]; hence, the over-screened orbital and spin fixed point lies on the line $g_T \approx \frac{n_a}{n_o}g_S \approx 5/2g_S$.

Fig. 1 summarizes the phases, and the Fe impurity forms an $S = 2$ local moment at a temperature $T \sim J_H$. Due to the Schrieffer mechanism for Kondo resonance narrowing, the orbital and spin Kondo temperatures are split, $(T_K^{orb}/D)^{2S} \sim T_K^{spin}/D$, and for $T_K^{orb} < T < T_K^{spin}$, the system flows towards a two channel orbital Kondo fixed point with MFL behaviour.




FIG. 4. Schematic plot of the RG flow. The perfectly screened hyper-spin Fermi liquid fixed point lies along the line $\beta_{g_T} = \alpha(S)g_s$ in plane I, and is stable against weak breaking of SU(4) symmetry [23]. For strong asymmetry, the system flows to the over-screened orbital and spin Kondo Fermi Liquid fixed point. The blue plane I is defined by $\beta_{g_m} = 0$, and the orange plane II is defined by $\beta_{g_T} = \alpha(g_m, S)\beta_{g_s}$. The bold line indicates the expected RG flow for a realistic FeAs tetrahedron.

At temperatures below T_K^{orb} , the orbital fluctuations in the e_g orbitals are quenched leaving an $S = 2$ spin interacting with five channels of conduction electrons. The system will first be screened from an $S = 2$ state to an $S = \frac{1}{2}$ or $S = 1$ state, depending on the relative strengths of the t_{2g} and e_g Kondo couplings; and will finally be completely screened at a lower temperature T_{K2}^{spin} . It is possible that these two scenarios could correspond to the chalcogenides and pnictides respectively.

In practice, real systems deviate from perfect tetrahedral symmetry, and breaking of the SU(2)^{orbital} symmetry would lift the e_g orbitals degeneracy via a Jahn-Teller splitting Δ_{JT} . It is well known from two channel Kondo physics that this will restore Fermi liquid behaviour below an energy scale Δ_{JT}^2/T_K^{orb} . This Fermi liquid behaviour will be seen only if $\Delta_{JT}^2/T_K^{orb} > T_{K1}^{spin}$. Raman spectroscopy indicates $\Delta_{JT} \sim 20 - 30$ meV [21], and $T_K \sim 0.1$ eV for some transition metals[24]. In general, we expect $T_K^{orb} > \Delta_{JT}$, meaning that the large T_K^{orb} will protect the system against breaking of the tetrahedral symmetry, thus preserving the critical over-screened phases for a range of applied pressures in experiments.

Various aspects of our theory could be tested in dilution experiments on materials such as $Ba(Ru_{1-x}Fe_xAs)_2$. The presence of local moment behaviour is expected to give rise to a Kondo resistance minimum. Our theory also predicts a logarithmic

temperature dependence of the orbital susceptibility, $\chi_o \sim \ln T$ below T_K^{orb} , which can be measured by resonant ultrasound spectroscopy, and a corresponding logarithmic divergence, $\chi_s \sim \ln T$, of the spin susceptibility below T_{K1}^{spin} . In addition, due to the series of MFLs that arise at T_K^{orb} and T_{K2}^{spin} , there would be a $C_v \sim T \ln T$ behaviour down to Δ_{JT}^2/T_K^{orb} .

The mechanisms for superconductivity and nematicity in the iron-based SCs remain open issues. We observe that critical orbital fluctuations within the e_g orbitals could provide a natural mechanism for nematic order. It is also known from studies of the over-screened single Kondo impurity[17, 25] that there is a divergent susceptibility for composite SC pairing and it remains an interesting question as to whether any of these divergent susceptibilities play a role in the dense materials.

We gratefully acknowledge discussions with Natan Andrei, Gabriel Kotliar, Zlatko Tesanovic and Jan Zaanen on aspects of this work. This work is supported by DOE grant DE-FG02-99ER45790.

-
- [1] Y. Kamihara, T. Watanabe, T. Hirano, and H. Hosono, J. Am. Chem. Soc. **130**, 3296 (2008).
 - [2] J.W. Lynn, and P. Dai Physica C **469**, 469 (2009).
 - [3] W.Z. Hu, *et. al.* Phys. Rev. Lett. **101**, 257005 (2008).
 - [4] D.N. Basov, *et. al.* Nat. Phys. **5**, 647 (2009).
 - [5] A. Tamai, *et. al.* Phys. Rev. Lett. **104**, 097002 (2010).
 - [6] Y. Xia, *et. al.* Phys. Rev. Lett. **103**, 037002 (2009).
 - [7] Q. Si, and E. Abrahams Phys. Rev. Lett. **101**, 076401 (2008).
 - [8] Z.P. Yin, K. Haule, and G. Kotliar Nat. Phys. **7**, 294 (2011).
 - [9] D. Basov, and A.V. Chubukov Nat. Phys. **7**, 272 (2011); P.J. Hirschfeld, M.M. Korshunov, and I.I. Mazin arXiv:1106.3712; D.J. Scalapino arXiv:1002.2413, and references therein.
 - [10] D.C. Johnston Adv. Phys. **59**, 803, (2010) and references therein.
 - [11] P. Dai, *et. al.* Nature Mat. **7**, 953 (2008).
 - [12] K. Yamada, *et. al.* J. Phys. Soc. Jpn **77**, 083704 (2008).
 - [13] M. Yamashita, *et. al.* arXiv:1103.0885
 - [14] S.K. Goh, *et. al.* Phys. Rev. B **82**, 094502 (2010).
 - [15] J.R. Schrieffer, J. Appl. Phys. **32**, 1143 (1967).
 - [16] A.H. Nevidomskyy, and P. Coleman Phys. Rev. Lett. **103**, 147205 (2009); P. Werner, E. Gull, M. Troyer, and A.J. Millis Phys. Rev. Lett. **101**, 166405 (2008); K. Haule, J.H. Shim, and G. Kotliar Phys. Rev. Lett. **100**, 226402 (2008)
 - [17] V.J. Emery, and S.A. Kivelson Phys. Rev. B **46**, 10812 (1992).
 - [18] P. Coleman, L.B. Ioffe, and A.M. Tsvelik Phys. Rev. B **52**, 6611 (1995).
 - [19] J.M. Maldacena, and A.W.W. Ludwig Nuc. Phys. B **506**, 565 (1997).
 - [20] J. Gan, N. Andrei, and P. Coleman Phys. Rev. Lett. **70**, 686 (1993).
 - [21] Z. Qin, *et. al.* Solid State Commun. **150**, 768 (2010).

- [22] K.I. Kugel, and D.I. Khomskii Sov. Phys. Usp. **25**, 231 (1982).
- [23] K. Le Hur, P. Simon, and L. Borda Phys. Rev. B. **69**, 045326 (2004).
- [24] M.D. Daybell, and W.A. Steyert Rev. Mod. Phys. **40**, 380 (1968).
- [25] V.J. Emery, and S.A. Kivelson Phys. Rev. Lett. **71**, 3701 (1993).